

Nomex<sup>®</sup> honeycomb was developed with the advent of the wide-body commercial airplane for use in flooring, bulkheads, dividers, galley structures and lavatories. General Veneer Manufacturing Co. was among the first to use it in production. Nomex<sup>®</sup> core offers high impact resistance and compressive properties and performs superbly on the food cart roller test.

General Veneer Manufacturing Co. has been supplying lightweight parts and raw materials to the Aircraft and Aerospace Industry for over 50 years.

## Geneerco #6, Type II

Geneerco #6 series is a non-metallic core bonded sandwich panel. This panel offers light weight, high performance, corrosion resistance, flame retardancy, impact resistance and cost effectiveness in one bonded sandwich panel with reinforced polymer or metallic faces. Although designed for use in flooring applications, these qualities make it

suitable for use in a wide range of applications. Fatigue testing indicates a long service life can be expected.

Geneerco #6, Type II, uses low density Nomex<sup>®</sup> honeycomb core, with Geneerco Phenoglass LS phenolic impregnated fiberglass skins.

Geneerco #6, Type II, meets the requirements of DAC Drawing S3933942 Types A and B.

*Geneerco Structures are available for many applications and installations that require quality products at a competitive cost. Please contact General Veneer Manufacturing Co. for more information regarding other available panel types.*


*As primary manufacturers of composite sandwich structures, we can help customers achieve maximum efficiency and cost-effectiveness when we also machine finished parts and add coatings, putty, and aerospace hardware.*

*Nomex<sup>®</sup> is a registered trademark of DuPont.*

## Geneerco #6, Type II

<b>Typical Physical and Mechanical Properties</b>		
<b>Physical Description</b>	<b>Typical Values</b>	<b>Unit</b>
<b>Geneerco #6</b>	<b>Type II</b>	
Weight	0.72	p.s.f.
Overall Thickness	0.350 to 0.375	in.
Top Skin Thickness	0.020 to 0.030	in.
Bottom Skin Thickness	0.020 to 0.030	in.
Nominal Core Density	6.0	p.c.f.
Core Cell Size	3/16	in.
Length • Nominal 96", 120", 144"	Up to 192	in.
Width • Nominal 48", 60", 72"	Up to 72	in.
Panels are available in other thicknesses, widths, lengths and core densities per customer request. Some widths may require skin splices.		

<b>Panel Strength • Test Method</b>	<b>Typical Values</b>	<b>Unit</b>
<b>Geneerco #6</b>	<b>Type II</b>	
Stabilized Compression • MIL-STD-401	1600	p.s.i.
Long Beam Bending • MIL-STD-401 (20 in. Span, 1/4 Point Loading)	320	lb.
Deflection at 100 lbs.	0.85	in.
Climbing Drum Peel • Standard Condition	30	in-lb/3-in. width
Flammability • 60 Sec. Vertical Ignition	12	sec.
Panel Shear 12" (L/W) • MIL-STD-401	585	lb.
Gardner Impact	35	in-lb
Meets the requirements of DAC Drawing S3933942, Types A and B.		
Geneerco Phenoglass LS face sheets are qualified to and meet the requirements of DMSI558, Type 2.		
Values listed represent theoretical averages to be expected. Prospective users should evaluate the material to determine if material is suitable for the users' specific requirements. User assumes all risk and responsibilities for any loss or damage caused by or resulting from the use of any information contained within this product bulletin.		



Need a part, not just a raw panel? General Veneer Manufacturing Co. can machine, drill, fill, prime, paint and add hardware to your product. We are a fully automatable shop, with 3 large CNC routers and a team of specialists for delicate custom work. Our finished parts fly daily and are launched into space on a regular basis.

General Veneer Manufacturing Co.

8652 Otis Street • P.O. Box 1607 • South Gate, California 90280 • U.S.A. • (323) 564-2661

www.generalveneer.com